




S MATIÈRES  
MARIUS AURENTI

2

Material – 08.26.2008



## MA's Waxed plaster coating

### Definition

Very fine finishing coat to be coloured in the mass or by applying a cast to water to create a decorative effect. White powder to be mixed with water and pigment and applied to gypsum blocks and dry partition, whether or not covered with old paintwork in good condition. Bases must be hard, sound, dry and clean. Old paintwork must be scraped or sanded.

### Preparation of the mixture

Incorporate the pigment (5% maximum) into 2 volumes of powder and slowly sprinkle the powder into 1 volume of water and allow to rest for a few minutes before mixing well mechanically. Wait 20 minutes before applying. We advise you to prepare the colouring for all surfaces to be coated in order to obtain a uniform appearance. Once prepared, the paste must be used within 12 hours (at 20 °C).

### Application of the coating

#### Primer

Apply the mixture using the smoothing tool or coating blade by superimposing the applications. Sand after complete drying (10 hours) with very fine paper.

#### Hydro

Apply in our saponified wax as a finish to protect and give a beautiful sheen.

### Conditions for application

Conformity with standards and regulations in force/Temperature above 8°C/Hygrometry less than 60% HR. Do not apply in an environment where condensation is likely to occur, or on a frozen or hot surface.

### Appearance

Waxed

### Output

From 0,5 kg/m<sup>2</sup> to 0,8 kg/m<sup>2</sup> according to the number of coats and the required appearance

### Maintenance

Cleaning with water.

### Composition

Mineral filler (calcium carbonate, re-dispersible resin and additives). Group III class 2. Not subject to labelling.

### Precautions

Use gloves/The final appearance and homogeneity of the colour depend on the regularity of the substrate and mixing as well as the implementation conditions. Store in a dry room away from frost and intense heat. All the information given in this technical sheet is given as for information only and shall not incur our responsibility. Tests must be carried out.