

Interior self levelling mortar

Mortar tinged in the mass with pigments and oxides intended for the realization of internal ground from 4 to 40 mm in thickness on new or ancient supports in concrete or dressed with a ceramic cover. Thanks to its mechanical resistances this MA's mortar is perfectly adapted to the heating grounds and to the premises with intense pedestrian traffic

Characteristics

Consisted of special cements with fast grip, of silica, resins and particular additives. After mixing in the water, it gives a fluid dough easy to implement manually or in the pump. This mortar hardens in some hours, quickly dries and acquires resistances raised to the flexion and to the compression. He allows to realize the finishes 48 hours later (temperature of 25°C °).

Directions for use

Supports will be clean, dry, solid, exempt from parts badly members (oil, fat, plaster painting, soft roe). On concrete raw as stone floor, apply our primary Epoxy (Let dry 3 hours in 20°C) before the application.

In a bowl containing approximately 4 liters of water, pour the 20 kg bucket by shaking in the mixer slow speed, until obtaining of a homogeneous mixture and without lumps (pH 12). Having to let rest(base) 5 min

After 5 minutes, mix briefly before the application. Prepare only the quantity to use in 20 minutes (in 23°C). This period is shorter if the temperature is higher. The implemented is made in a single pass from 4 to 40 mm by means of a metal spatula or of a Flemish lisseuse. The passage of the roller to débulleur is not necessary.

Respect the joints of dilation of the support.

Realize joints of division all 50 m². Weight of the mixture 2kg /dm³ approximately.

Period of use in 23°C: approximately 15 minutes / time of grip 90 minutes / Use pedestrian 4 hours

Precautions of application:

Do not add water after the beginning of grip, not add lime, cement, plaster or other. Do not apply to support subject to humidity. Do not apply to surfaces presenting some stagnant water. Do not apply if the temperature is lower in +5°C and superior in 30°C

Coverage: 1.7 kg /mm/m²

Entretien : nettoyage à l'eau.

Conditioning: jar of 5 and 20 kg

Colours : 51 mineral colours

Aspect : Matt, silky, brilliant

Maintenance: Clean the tools with water before the product hardens.

This product contains cements and can provoke irritations. Use gloves. The final aspect and the homogeneity of the tint depend on the regularity of the support of the kneading and on the conditions of the implemented.

Preserve shielded from the frost, strong hot season and in a dry premises / All the information presented in this technical sheet is given as information and cannot engage our responsibility.

Always test before use.